


Quartz Glass for Lamps

Compared with ordinary glass materials, quartz glass has superior light transmittance and high temperature stability characteristics. Thus, quartz glass is widely used in various lamps, including mercury lamps, halogen lamps, xenon lamps, and so on.

Lamps in which quartz glass is used are employed in numerous different fields. For example, these lamps are used for sterilization in the foodstuffs and medical treatment industries, as light sources in all types of lighting, optical equipment, and in the exposure devices used in semiconductor manufacturing processes, and as lamps used in cleaning applications, etc.

Shin-Etsu Quartz Products Co., Ltd. offers a broad line-up, from natural quartz glass and ozone-free quartz glass all the way to ultra-high purity synthetic quartz glass suitable for use in vacuum and ultraviolet regions.

Thus, you can select the material that is optimal for the application use you desire.



Quartz Glass for Lamps: Product Types

Quartz glass is well suited to lamp-usage for its superior light transmittance and heat-resistance characteristics. Shin-Etsu Quartz Products Co., Ltd offers the following products for lamp-usage quartz glass tubes: Ozone-free quartz glass, Natural quartz glass and Synthetic quartz glass. All of these are made using the Company's unique "tool-free" method, enabling smooth and flat inner and outer surfaces without any flaws. We can manufacture quartz glass tubes for lamps in suitable size and in small lots.

Ozone-Free Quartz Glass: M235 & M215

M235 and M215 are ozone-free quartz glass whereby, through doping with a special oxidized metal, the light transmittance characteristics for ultraviolet waves are controlled and reduced. At wavelengths of 235 nm and shorter, M235 shows reduced light transmittance of 50% or less, while M215 has 50% or less reduced light transmittance at wavelengths of 215 nm and shorter.

Synthetic Quartz Glass: SUPRASIL-300 & SUPRASIL-310

SUPRASIL-300 and SUPRASIL-310 brands of synthetic quartz glass are bubble-free, and they have an ultra-high purity well beyond that of natural quartz glass. These brands also have superior light transmittance characteristics in ranges from vacuum ultraviolet to infrared. SUPRASIL-300 is synthetic quartz glass with no OH base, while SUPRASIL-310 is synthetic quartz glass containing OH base at approximately 250 ppm.

Natural Quartz Glass: HERALUX, HLQ210 & HLQ270

HERALUX is a liquid-type natural quartz glass product made by oxyhydrogen flame melting, and HLQ210 and HLQ270 are non-liquid-type natural quartz glass products made by electrical melting. Especially, HLQ270 is a high purity natural quartz glass product for lamps from which metallic impurities (and especially alkali metals) have been removed using a special refining process.

Product Types

Category	Grade	OH Content (ppm)	Characteristics	Shape
Ozone-Free Quartz Glass	M235, M215	approx. 130 to 220	M235 shows reduced light transmittance of 50% or less at wavelengths of 235 nm and shorter, while M215 has 50% or less reduced light transmittance at wavelengths of 215 nm and shorter.	Tube
Synthetic Quartz Glass	SUPRASIL-300	< 1	An ultra-pure product, without any bubbles or foreign matter.	Tube
	SUPRASIL-310	approx.250	Its transmittance characteristics are superior especially at vacuum ultraviolet wavelengths.	Tube, Plate
Natural Quartz Glass	HERALUX	approx.170	This shows superior transmittance characteristics at wavelengths of 200 nm and above.	Tube, Plate, Rod
	HLQ210, HLQ270	approx.30		

* Please note that for some discharge lamps, quartz glass containing OH base cannot be used. For these types of applications, we also handle the HLQ-200 series with low OH base content (imported from the German company, Heraeus).

Measured Transmission

Figure 1 SUPRASIL-300, SUPRASIL-310





Figure 2 M-235, M382



* Reference data for a sample with 2 mm thickness and mirror-surface finishing

Product inquiries



<https://www.sqp.co.jp/e/>

Shin-Etsu Quartz Products Co., Ltd.

Functional Materials Division

Shinjuku San-ei Bldg., 1-22-2, Nishi-Shinjuku, Shinjuku-ku, Tokyo 160-0023, Japan
 TEL : +81-3-3348-1916 FAX : +81-3-3348-4919